

## Product Description

**HYOSUNG Polypropylene R401E** is specially designed polypropylene random copolymer that features high transparency, gloss, and processibility. It is suitable for thermoforming food containers, stationaries, and EBM bottles.

## Application

EBM bottles  
 Transparent thermoforming sheet  
 Stationaries

## Features

High transparency  
 High gloss  
 Phthalate free

## Properties

Properties	Test Method	Typical Value	Unit
<b>Resin Properties</b>			
Melt Index(230°C, 2.16kg)	ASTM D1238 ISO 1133	2.8	g/10min
Density	ASTM D792 ISO 1183	0.90	g/cm <sup>3</sup>
<b>Mechanical Properties</b>			
Tensile Strength at Yield	ASTM D638 ISO 527	310 28	kg/cm <sup>2</sup> MPa
Flexural Modulus	ASTM D790 ISO 178	11,000 940	kg/cm <sup>2</sup> MPa
Izod Impact Strength, Notched at 23°C	ASTM D256	9.0	kg·cm/cm
Charpy Impact Strength at 23°C	ISO 179/1eA	7.0	kJ/m <sup>2</sup>
Rockwell Hardness	ASTM D785	85	R-Scale
Heat Deflection Temperature (0.45MPa)	ASTM D648	100	°C
VICAT Softening Temperature (10N)	ASTM D1525	125	°C
Haze (2mm)	ASTM D1003	20	%

\* The values listed above are typical values for reference purpose only and shall not be construed as specifications.

## Storage and Handling

This product should be stored in dry condition at temperature below 40°C and protected from UV-light. When condensation is visible or can be expected, pre-drying is recommended. (Drying condition: 80~100°C / 2~4hours at air circulated condition)


## Disclaimer

All information, including product characteristics, applications and properties are for reference purpose only and shall not be construed as specifications. Before using this product, customers should carefully review the instructions for use of the product to determine whether the product is suitable for the customer's particular purpose. The customer is responsible for the appropriate, safe and legal use, processing and handling of this product. HYOSUNG CHEMICAL CORPORATION assumes no legal responsibility or liability for the contents of this document. We reserve the right to change the contents of this document without prior notice. This document is copyrighted by HYOSUNG CHEMICAL CORPORATION.

## Contacts

**Head Office** (06578) 235, Banpo-daero, Seocho-gu, Seoul, KR  
 Tel: +82-2-2146-5439  
**Online** www.hyosungchemical.com

**Processing Parameters**



Specifications	Unit	Recommended Parameters
Feed Zone Temperature	°C	160 ~ 180
Melting Zone Temperature	°C	180 ~ 225
Metering Zone Temperature	°C	180 ~ 250
Die or Nozzle Temperature	°C	180 ~ 250
Mold Temperature (for EBM)	°C	180 ~ 220
Screw Speed	rpm	15 ~ 50
Blowing Pressure (for EBM)	psi	90

**Considerations**

Due to variations in screw design and heat efficiency according to types of facilities, optimal conditions for each facility may differ. Therefore, the optimal temperature conditions for each facility must be taken into consideration depending on thickness of intermediate or final product, extruding pressure, cooling efficiency, changes in MI of the final product, appearances of the final product, and others.

**Health, Safety and Food Contact Regulations**

PP R401E complies with FDA requirements in the code of Federal Regulations in 21 CFR 177. 1520 for food contact and European Commission Regulation (EU) No 10/2011 and its amendments up to (EU) No 2023/1627 with regard to plastic materials and articles intended to come into contact with food.

**Energy Savings**

PP R401E provides improved aesthetics at significantly lower process temperatures that leads to lowered energy consumptions, shortened cycle time and improved productivity. It enables an average of 10% energy savings for production of clarified PP parts.

Milliken  
**Millad<sup>®</sup> NX<sup>™</sup> 8000**  
 The New Standard In Clear Polypropylene



**Contacts**

**Head Office** (06578) 235, Banpo-daero, Seocho-gu, Seoul, KR  
 Tel: +82-2-2146-5439  
**Online** www.hyosungchemical.com