

Polypropylene Random Terpolymer  
For Medical applications

### Product Description

*Topilene*® R430CN is a polypropylene random terpolymer that features excellent transparency and gloss. This grade is designed for medical applications like medical port/cap and IV solution bag and BOPP.

*Topilene*® R430CN does not contain film additives like slip and antiblocking agents.

### Characteristics

**Typical Application** Medical port/cap / Medical film / IV solution bag/ BOPP

**Features** High transparency / Phthalate-Free / Bisphenol Free / Excellent gloss

### Typical Properties

Characteristics	Method	Value	Unit	
<b>Physical</b>				
Melt Index(230°C, 2.16kg)	ASTM D1238	<b>5.0</b>	g/10min	
Density	ASTM D792	<b>0.90</b>	g/cm <sup>3</sup>	
<b>Mechanical</b>				
Tensile Strength at Yield	ASTM D638	<b>230</b>	kg/cm <sup>2</sup>	
Flexural Modulus	ASTM D790	<b>7,000</b>	kg/cm <sup>2</sup>	
Notched Izod Impact Strength(23°C)	ASTM D256	<b>7.5</b>	kg·cm/cm	
Rockwell Hardness	ASTM D785	<b>80</b>	R-scale	
<b>Thermal</b>				
Melting Temperature	HS Method	<b>132</b>	°C	
Heat Seal Initiation Temperature	HS Method	<b>105</b>	°C	
<b>Additional Properties</b>				
Haze	30um film	ASTM D1003	<b>&lt;2.0</b>	%

The values listed above are typical values for reference purpose only and shall not be construed as specifications.

### Contacts

**Head Office**

Lot 01CN ~ 08CN, Cai Mep Industrial Park,  
Tan Phuoc Ward, Phu My Town, Ba Ria Vung Tau  
Province, Vietnam.

Tel: +84-254-393-7949 Fax: +84-254-393-7849

**Online**

www.hyosungchemical.com  
www.topilene.com



Polypropylene Random Terpolymer  
For Medical applications

### Health, Safety and Food Contact Regulations

---

*Topilene*<sup>®</sup> R430CN complies with FDA requirements in the code of Federal Regulations in 21 CFR 177. 1520 for food contact and European Commission Regulation (EU) No 10/2011 and its amendment (EU) No 2016 / 1416 with regard to plastic materials and articles intended to come into contact with food.

### Storage and Handling

---

This product should be stored in dry condition at temperature below 40°C and protected from UV-light. When condensation is visible or can be expected, pre-drying is recommended. (Drying condition: 80~100°C/2~4hours at air circulated condition)

### Disclaimer

---

All information, including product characteristics, applications and properties are for reference purpose only and shall not be construed as specifications. Before using this product, customers should carefully review the instructions for use of the product to determine whether the product is suitable for the customer's particular purpose. The customer is responsible for the appropriate, safe and legal use, processing and handling of this product. HYOSUNG VINA CHEMICALS CORPORATION assumes no legal responsibility or liability for the contents of this document. We reserve the right to change the contents of this document without prior notice. This document is copyrighted by HYOSUNG VINA CHEMICALS CORPORATION. *Topilene*<sup>®</sup> is a registered trademark owned or used by HYOSUNG VINA CHEMICALS CORPORATION.

### Contacts

---

#### Head Office

Lot 01CN ~ 08CN, Cai Mep Industrial Park,  
Tan Phuoc Ward, Phu My Town, Ba Ria Vung Tau  
Province, Vietnam.

Tel: +84-254-393-7949 Fax: +84-254-393-7849

#### Online

[www.hyosungchemical.com](http://www.hyosungchemical.com)  
[www.topilene.com](http://www.topilene.com)

