HYOSUNG VINA CHEMICALS

TECHNICAL DATA SHEET

Topilene® R500F

Polypropylene Random Copolymer For CPP Film

Product Description

Topilene[®] **R500F** is random polypropylene for casting film application. This grade is designed to potential end use CPP film applications for core and sealing layer. It exhibits good transparency, high gloss and excellent heat sealing strength.

Characteristics

Typical Application Semi retort pouch

Features Good transparency / high gloss / Excellent heat sealing strength

Typical Properties

| Characteristics | Method | Value | Unit |
|------------------------------------|------------|-------|----------|
| Physical | | | : |
| Melt Index(230°C, 2.16kg) | ASTM D1238 | 7.5 | g/10min |
| Density | ASTM D792 | 0.90 | g/cm³ |
| Mechanical | | | |
| Tensile Strength at Yield | ASTM D638 | 280 | kg/㎝² |
| Flexural Modulus | ASTM D790 | 9,500 | kg/cm² |
| Notched Izod Impact Strength(23°C) | ASTM D256 | 5.0 | kg·cm/cm |
| Rockwell Hardness | ASTM D785 | 85 | R-scale |
| Thermal | | | |
| Melting Temperature | ASTM D1525 | 145 | °C |
| Crystallization Temperature | ASTM D1525 | 105 | °C |
| Film(40um) | | | |
| Haze | ASTM D1004 | 1.0 | % |

The values listed above are typical values for reference purpose only and shall not be construed as specifications.

Contacts

| Head Office | Lot 01CN ~ 08CN, Cai Mep Industrial Park, Tan Phuoc Ward, Phu My Town, Ba Ria Vung Tau Province, Vietnam. | |
|-------------|---|-------------------|
| Online | Tel: +84-254-393-7949 Fax: +84-254-393-7849 www.hyosungchemical.com www.topilene.com | PHTHALATE FREE |

HYOSUNG VINA CHEMICALS

TECHNICAL DATA SHEET

Topilene° R500F

Polypropylene Random Copolymer For CPP Film

Health, Safety and Food Contact Regulations

Topilene[®] **R500F** complies with FDA requirements in the code of Federal Regulations in 21 CFR 177. 1520 for food contact.

Storage and Handling

This product should be stored in dry condition at temperature below 40°C and protected from UV-light. When condensation is visible or can be expected, pre-drying is recommended. (Drying condition: 80~100°C/2~4hours at air circulated condition)

Disclaimer

All information, including product characteristics, applications and properties are for reference purpose only and shall not be construed as specifications. Before using this product, customers should carefully review the instructions for use of the product to determine whether the product is suitable for the customer's particular purpose. The customer is responsible for the appropriate, safe and legal use, processing and handling of this product. HYOSUNG VINA CHEMICALS CORPORATION assumes no legal responsibility or liability for the contents of this document. We reserve the right to change the contents of this document without prior notice. This document is copyrighted by HYOSUNG VINA CHEMICALS CORPORATION. *Topilene*® is a registered trademark owned or used by HYOSUNG VINA CHEMICALS CORPORATION.

Contacts

| Head Office | Lot 01CN ~ 08CN, Cai Mep Industrial Park, Tan Phuoc Ward, Phu My Town, Ba Ria Vung Tau Province, Vietnam. | |
|-------------|---|-------------------|
| Online | Tel: +84-254-393-7949 Fax: +84-254-393-7849 www.hyosungchemical.com www.topilene.com | PHTHALATE FREE |