



**CONTROLLED  
DOCUMENT**

Shintech Inc., 5618 Highway 332 East, Freeport, Texas 77541, (979) 233-7861

**Polyvinyl Chloride Resin  
Product Specifications**

Effective Date: 06/02/14  
 Supersedes: 03/03/03

**SE-1300**

General Description

Type : Polyvinyl Chloride Homopolymer  
 Polymerization Process : Suspension  
 Appearance : White, free flow powder

Features and Uses

Extrusion : Tubing, Flex Sheet, Wire & Cable, Profile  
 Calendering Film, Sheet

Specification

Resin Properties	Unit	Specification Range	Test Method
Inherent Viscosity		1.020 – 1.050	ASTM D 1243
K Value ❶		71.5 – 72.9	ISO 1628-2
Bulk Density	lbs./ft. <sup>3</sup>	30.5 – 33.5	ASTM D 1895
	g /cc	0.488 – 0.537	
Particle Size	%		ASTM D 1921
40 mesh on		0.5 maximum	
pan		5.0 maximum	
Average Particle Size	micron		ASTM D 1921
Volatile	%	0.3 maximum	ASTM D 3030
Residual VCM	ppm	1.0 maximum	EPA 107
Foreign Matter		15 maximum	QAWT 1008
(250g PVC/Liter of water)			
Resin Color( Hunter)			QAWT 1015
L value		97.2 minimum	
a value		0.5 maximum	
b value		1.5 maximum	
Fisheyes		15 maximum	QAWT 1012

❶ K Value (reference) from a viscosity conversion table.

Shintech warrants only that the product will comply with the foregoing specifications. All other warranties, expressed and implied, including the implied warranties of merchantability and fitness for a particular purpose, are expressly disclaimed. While "Typical Value" represents Shintech's experience with respect to the resin's properties, no warranty is given that the product will achieve Typical Values; Shintech only warrants that the product will be within the applicable specification range.