



**CONTROLLED
DOCUMENT**

Shintech Inc., 5618 Highway 332 East, Freeport, Texas 77541, (979) 233-7861

**Polyvinyl Chloride Resin
Product Specifications**

Effective Date: 06/02/14
 Supersedes: 03/03/03

SE-750A

General Description

Type : Polyvinyl Chloride Homopolymer
 Polymerization Process : Suspension
 Appearance : White, free flow powder

Features and Uses

Extrusion : Film, Sheet, and Profile
 Calendaring : Sheet and Film

Specification

Resin Properties	Unit	Specification Range	Test Method
Inherent Viscosity		0.725 – 0.755	ASTM D 1243
K Value ❶		58.4 – 59.7	ISO 1628-2
Bulk Density	lbs./ft. ³	35.0 – 38.0	ASTM D 1895
	g /cc	0.560 – 0.610	
Particle Size	%		ASTM D 1921
40 mesh on		0.5 maximum	
pan		5.0 maximum	
Average Particle Size	micron		ASTM D 1921
Volatile	%	0.3 maximum	ASTM D 3030
Residual VCM	ppm	1.0 maximum	EPA 107
Foreign Matter		15 maximum	QAWT 1008
(250g PVC/Liter of water)			
Resin Color(Hunter)			QAWT 1015
L value		97.0 minimum	
a value		0.5 maximum	
b value		1.5 maximum	
Fisheye		15 maximum	QAWT 1013

❶ K Value (reference) from a viscosity conversion table.